

(19)  Canadian
Intellectual Property
Office

An Agency of
Industry Canada

Office de la Propriété,
Intellectuelle
du Canada

Un organisme
d'Industrie Canada

(11) **CA 2 474 143** (13) **A1**

(40) 08.04.2004
(43) 08.04.2004

(12)

(21) **2 474 143**

(22) **26.09.2003**

(51) Int. Cl. 7: **B32B 27/18, C08J 5/18,
B32B 27/32**

(85) **29.07.2004**

(86) **PCT/CA03/001483**

(87) **WO04/028800**

(30) **60/413,454 US 26.09.2002**

(71) **MARKO I.R.D.C. INC.,
9340 Meaux Street, ST. LEONARD, Q1 (CA).**

**LEFEBVRE, JULIEN (CA).
GARROCHO, JOSE (CA).
FROHLICH, MARK (CA).
LEPLATOIS, LUDOVIC (CA).**

(72)

(74) **OSLER, HOSKIN & HARCOURT LLP**

(54) **FILM ELASTOMERE A ADDITIF ANTIDERAPANT**

(54) **ELASTOMERIC FILM HAVING ANTI-SKID ADDITIVE**

(57)

The present invention provides an elastomeric film having anti-skid properties. The film comprises one or more layers, wherein at least one of the layers comprises from 0.1 to 10% (by weight) of an anti-skid additive, which does not melt, or has a melt temperature greater than 500 °F, and has a particle size between 50 and 500 microns. Suitable anti-skid additives may be sand, clay, silica, crosslinked polyethylenes, other polymers or ultra high molecular weight polyethylene (UHMWPE). Also provided is a resin composition and a method for manufacturing an elastomeric film having anti-skid properties.



Office de la Propriété
Intellectuelle
du Canada

Un organisme
d'Industrie Canada

Canadian
Intellectual Property
Office

An agency of
Industry Canada

CA 2474143 A1 2004/04/08

(21) **2 474 143**

(12) **DEMANDE DE BREVET CANADIEN
CANADIAN PATENT APPLICATION**

(13) **A1**

(86) Date de dépôt PCT/PCT Filing Date: 2003/09/26

(87) Date publication PCT/PCT Publication Date: 2004/04/08

(85) Entrée phase nationale/National Entry: 2004/07/29

(86) N° demande PCT/PCT Application No.: CA 2003/001483

(87) N° publication PCT/PCT Publication No.: 2004/028800

(30) Priorité/Priority: 2002/09/26 (60/413,454) US

(51) Cl.Int.⁷/Int.Cl.⁷ B32B 27/32, C08J 5/18

(71) Demandeur/Applicant:
MARKO I.R.D.C. INC., CA

(72) Inventeurs/Inventors:
LEFEBVRE, JULIEN, CA;
GARROCHO, JOSE, CA;
FROHLICH, MARK, CA;
LEPLATOIS, LUDOVIC, CA

(74) Agent: OSLER, HOSKIN & HARCOURT LLP

(54) Titre : FILM ELASTOMERE A ADDITIF ANTIDERAPANT

(54) Title: ELASTOMERIC FILM HAVING ANTI-SKID ADDITIVE

(57) Abrégé/Abstract:

The present invention provides an elastomeric film having anti-skid properties. The film comprises one or more layers, wherein at least one of the layers comprises from 0.1 to 10% (by weight) of an anti-skid additive, which does not melt, or has a melt temperature greater than 500 °F, and has a particle size between 50 and 500 microns. Suitable anti-skid additives may be sand, clay, silica, crosslinked polyethylenes, other polymers or ultra high molecular weight polyethylene (UHMWPE). Also provided is a resin composition and a method for manufacturing an elastomeric film having anti-skid properties.

Canada

<http://opic.gc.ca> • Ottawa-Hull K1A 0C9 • <http://cipn.gc.ca>

OPIC • CIPN 191

OPIC



CIPN

CA2474143

Publication Title:

ELASTOMERIC FILM HAVING ANTI-SKID ADDITIVE

Abstract:

Abstract of CA2474143

The present invention provides an elastomeric film having anti-skid properties. The film comprises one or more layers, wherein at least one of the layers comprises from 0.1 to 10% (by weight) of an anti-skid additive, which does not melt, or has a melt temperature greater than 500 °F, and has a particle size between 50 and 500 microns. Suitable anti-skid additives may be sand, clay, silica, crosslinked polyethylenes, other polymers or ultra high molecular weight polyethylene (UHMWPE). Also provided is a resin composition and a method for manufacturing an elastomeric film having anti-skid properties. Data supplied from the esp@cenet database - Worldwide

Courtesy of <http://v3.espacenet.com>